

CCI



ADMIX GROUT-II™

NON-SHRINK, FREE FLOWING, SELF LEVELLING,
ULTRA HIGH STRENGTH CEMENTITIOUS GROUT.

PRODUCT	Single pack ready to use, non-shrink, free flowing, self levelling, ultra high strength, cementitious grout designed with a blend of specially processed cement and fillers, without corrosive substances.																	
BENEFITS	Non-shrink characteristics, retain original volume by expansion. Free flowing, self-levelling grout easily filling under-bases of machinery. Pre packed batches ensure consistent material and only addition of water required at site. Excellent adhesion to concrete and steel. Non-metallic & chloride free.																	
USES	Bolt pockets and base plate grouting of all equipments. Grouting of stanchion bases of all types of machinery with dynamic load in industries or industrial projects.																	
DESCRIPTION	ADMIX GROUT II is based on specially processed cement, fillers and additives. It is ready to use component and only addition of water required at site. 25 kg ADMIX GROUT II requires 4.25 ltr of water for pourable and 4.50 ltr for flowing grout.(Max.) Water powder (w/p) ratio is 0.17 and 0.18 respectively. ADMIX GROUT II is suitable for thickness between 10mm to 50mm. However in excess of 50mm thickness, cleaned and washed 10mm aggregate can be incorporated to the mix at the rate of 50% to 100% of the quantity of grout used. Controlled expansion takes place in the unset material to ensure that the grout, when cured, will continue to occupy its original volume. For thicker section it is necessary to incorporate well graded and washed aggregate in to the grout to reduce heat build-up.																	
STRENGTH DEVELOPMENT	<p>The compressive strength development of ADMIX GROUT II, generally found to be as follows:</p> <table border="1" data-bbox="613 1675 1445 1879"> <thead> <tr> <th rowspan="2">AGE IN DAYS</th> <th colspan="2">COMPREHESIVE STRENGTH IN kg /cm²</th> </tr> <tr> <th>POURABLE W/P O.17</th> <th>FLOWABLE W/P O.19</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>300</td> <td>250</td> </tr> <tr> <td>3</td> <td>375</td> <td>350</td> </tr> <tr> <td>7</td> <td>500</td> <td>450</td> </tr> <tr> <td>28</td> <td>700</td> <td>650</td> </tr> </tbody> </table> <p>-----</p> <p>7.07cm x 7.07cm size restrained cubes were tested</p>	AGE IN DAYS	COMPREHESIVE STRENGTH IN kg /cm ²		POURABLE W/P O.17	FLOWABLE W/P O.19	1	300	250	3	375	350	7	500	450	28	700	650
AGE IN DAYS	COMPREHESIVE STRENGTH IN kg /cm ²																	
	POURABLE W/P O.17	FLOWABLE W/P O.19																
1	300	250																
3	375	350																
7	500	450																
28	700	650																

PRODUCT PROPERTIES	Yield per 25 kg : 12.5 ltr approx. Pourable life : 15 minutes max. Application : 10°C to 40°C, Expansion (% Vol) 0.8 to 1.5, Flow on flow table: 17 to 22cms.
PACKING & SHELF LIFE	Available in 25 kg HDPE bags. Minimum 6 months from the date of manufacturing if stored in original container under shade, unopened.
QUALITY ASSURANCES	CCI INC., is an ISO 9001-2015 certified company and our products are in accordance with international standards.



CCI INC.

No. 41, CCI House, 7th B Jakkur Cross, Opp: St .John's School,
Amruthahalli, BENGALURU- 560 092. Phone: +91 80 68997002
Website: www.cciadditives.com / www.ccichemicals.com
Email : info@ccichemicals.com sales@ccichemicals.com
Customer Support: +91 9481906617 / +91 80 68997002
An ISO 9001-2015 Certified Company

CCI 2016-17 admix grout-II



AN ISO 9001 - 2015 CERTIFIED COMPANY

The information given in this data sheet is based on both current development and many years of field experience. While every effort is made to ensure that the information is reliable, we can not accept responsibility of any work carried out with our products as we have no control over the application procedure adopted at site and site conditions. In view of continuous research and development in our laboratory, we advise customers ,in their own interest, to ensure that this data sheet has not been superseded by any other publication. Field services where provided, does not constitute supervisory responsibility. For additional information, CCI Inc local representative or customer care department may be contacted.