

CCI



LEAKGUARD -C SUPER™

TWO PART ACRYLIC POLYMER MODIFIED
CEMENTITIOUS WATERPROOF COATING SYSTEM

PRODUCT	Two part (powder + liquid – high density), pre-packed, acrylic polymer modified cementitious new generation waterproof coating.
BENEFITS	Pre-packed product to ensure perfect proportion of mixing, excellent waterproofing characteristics, excellent adhesion, flexible layer, cost effective waterproofing system.
PACKING	LEAKGUARD-C SUPER is packed in two separate components in 9 kg powder and 5 ltr liquid of high density.
USES	All concrete structures like Roof tops, basements, water tanks, sunken slabs, swimming pools, retaining walls, slope roofs etc. LEAKGUARD-C SUPER can also be used for coatings on asbestos sheets and those areas where large section coating is required.
MIXING	LEAKGUARD-C SUPER should preferably be mixed mechanically to ensure uniform mixing for better cohesive consistency. Take out the liquid portion of LEAKGUARD-C SUPER to a bucket and slowly add powder portion while mixing is on. Mix it thoroughly till a homogenous paint consistency is formed. Mixed LEAKGUARD-C SUPER should be used/consumed within 10 to 15 minutes. (max). STD conforms to: ASTM D4060 / ASTM D4541 / ASTM D 638 / ASTM C836.
COVERAGE & SHELF LIFE	LEAKGUARD-C SUPER gives a coverage of above 300 and above sft per pack, single coat. (5Ltr liquid of high density and 9 kg powder.) LEAKGUARD-C SUPER can be stored in original sealed pack under shade in dry condition for 24 months.

<p>APPLICATION PROCEDURE</p>	<p>Surface preparation : Surface should be cleaned thoroughly by using wire brush and all loose particles, oil stains if any, dust, paint etc., should be removed and cleaned by sufficient quantity of water. Un-plastered, un-even surfaces or any cracks on the surface should be repaired to make it even for better bonding. Surface should be strong & sound.</p> <p>Application : The prepared surface should be sufficiently wet and water stagnation if any, should be removed. Then mixed LEAKGUARD-C SUPER to be applied uniformly by brush both vertical and horizontal directions, one by one. Two or three coats are recommended.</p>
<p>ADDITIONAL INFORMATION</p>	<p>One extra coat of LEAKGUARD-C SUPER is recommended on the junctions and joints especially parapet wall bottom joints on rooftops. Slight water sprinkling on the first coat is recommended before starting second and subsequent coats.</p>
<p>WATER CURING</p>	<p>Light sprinkling of water for 2 to 3 times on LEAKGUARD-C SUPER applied surface for the first day will benefit into added advantage.</p>
<p>QUALITY ASSURANCES</p>	<p>CCI INC., is an ISO 9001-2015 certified company and our products are in accordance with international standards.</p>



CCI INC.

No. 41, CCI House, 7th B Jakkur Cross, Opp: St .John's School,
Amruthahalli, BENGALURU- 560 092. Phone: +91 80- 68997002
Website: www.cciadditives.com / www.ccichemicals.com
Email : info@ccichemicals.com sales@ccichemicals.com
Customer Support: +91 9481906617 / +91 80 68997002
An ISO 9001-2015 Certified Company

CCI 2016-18 - leakguard c super



The information given in this data sheet is based on both current development and many years of field experience. While every effort is made to ensure that the information is reliable, we can not accept responsibility of any work carried out with our products as we have no control over the application procedure adopted at site and site conditions. In view of continuous research and development in our laboratory, we advise customers ,in their own interest, to ensure that this data sheet has not been superseded by any other publication. Field services where provided, does not constitute supervisory responsibility. For additional information, CCI Inc local representative or customer care department may be contacted.